



# **Gasketseal Black**

Revision: 30/08/2017 Page 1 from 2

# **Technical data**

Basis	Polysiloxane
Consistancy	Stable paste
Curing system	Moisture curing
Skin formation* (20°C / 65% R.H.)	Ca. 10 min
Curing speed * (20°C / 65% R.H.)	Ca. 2 mm/24h
Hardness	30 ± 5 Shore A
Density	1,05 g/ml
Elastic recovery (ISO 7389)	> 80 %
Max. tension (DIN 53504)	2,00 N/mm²
Elasticity modulus 100% (DIN 53504)	Ca. 0,60 N/mm <sup>2</sup>
Elongation at break (DIN 53504)	> 500 %
Temperature resistance	-60 °C → 285 °C
Application temperature	$5 ^{\circ}\text{C} \rightarrow 35 ^{\circ}\text{C}$

<sup>(\*)</sup> these values may vary depending on environmental factors such as temperature, moisture, and type of substrates.

# **Product description**

Gasketseal Black is a temperature resistant, elastic, one-component silicone sealant and replaces all cork, felt, fiber, paper and rubber gaskets in all thicknesses and widths.

# **Properties**

- Excellent resistance to fuels, oils and
- High temperature resistance
- Very easy to apply
- Permanently elastic after curing
- Typical acetic smell

# **Applications**

- Formation of gasket and sealing rings.
- Sealing between metal components.
- Sealing of heating installations.

# **Packaging**

Colour: black

Packaging: 310 ml cartridge, other packaging on request

#### Shelf life

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

#### Chemical resistance

Good resistance to water, aliphatic solvents, mineral oils, grease, diluted inorganic acids and alkalis. Poor resistance to aromatic solvents, concentrated acids and chlorinated hydrocarbons.

### **Substrates**

Substrates: metals

Nature: clean, dry, free of dust and grease. Surface preparation: No pretreatment required. We recommend a preliminary adhesion test on any substrate.

# **Application method**

Application method: With manual- or pneumatic caulking gun.

Cleaning: Clean with White Spirit or Soudal Surface Cleaner immediately after use (before curing).

Finishing: With a soapy solution or Soudal Finishing Solution before skinning.

Repair: With the same material

# **Health- and Safety Recommendations**

Take the usual labour hygiene into account. Consult the packaging label for more information.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

Soudal NV Everdongenlaan 18 - 20 BE-2300 Turnhout Tel: +32 (0)14-42.42.31 Fax: +32 (0)14-42.65.14 www.soudal.com





# **Gasketseal Black**

Revision: 30/08/2017 Page 2 from 2

#### Remarks

• Because of the acid nature, certain metals (eg copper, lead) can be affected.

# Liability

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

 Soudal NV
 Everdongenlaan 18 - 20
 BE-2300 Turnhout

 Tel: +32 (0)14-42.42.31
 Fax: +32 (0)14-42.65.14
 www.soudal.com