



Sanitary Silicone Turbo

Revision: 3/08/2020 Page 1 from 2

Technical data

100111100110011	
Basis	Polysiloxane
Consistency	Stable paste
Curing system	Moisture curing
Skin formation* (23°C/50% R.H.)	Ca. 7 min
Curing speed * (23°C/50% R.H.)	Ca. 4 mm/24h
Hardness**	23 ± 5 Shore A
Density**	Ca. 1.03 g/ml
Elastic recovery (ISO 7389)**	> 90 %
Maximum allowed distortion (ISO 11600)	25 %
Max. tension (ISO 37)**	0,70 N/mm²
Elasticity modulus 100% (ISO 37)**	0,30 N/mm²
Elongation at break (ISO 37)**	400 %
Temperature resistance**	-60 °C → 180 °C
Application temperature	5 °C → 35 °C

^{*} These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. ** This information relates to fully cured product.

Product description

Sanitary Silicone Turbo is a high quality, elastic, 1-component joint sealant based on silicones with a curing speed 3 times faster than regular silicones.

Properties

- Very fast in depth curing
- Can be loaded faster due to its faster curing
- Impervious to mould
- Very easy to apply
- · Colourfast and UV resistant
- Very good adhesion on sanitary surfaces
- Permanently elastic after curing
- Typical acetic smell

Applications

- For sealing of joints in sanitary and other moist rooms between e.g.. showers, bathtubs and (tiled) walls, between walls and washbasins, between floors and toilet.
- · Joints in kitchens.
- Joints in cold stores.

Packaging

Colour: white

Packaging: 290 ml cartridge, 300 ml cartridge

Shelf life

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

Substrates

Substrates: all usual building substrates, enamel, ceramic tiles, glass, wood, Galvanised metals, aluminium, no pvc, no acrylic bathtubs

Nature: rigid, clean, dry, free of dust and grease.

Surface preparation: Porous surfaces should be primed with Primer 150. No primer needed for non-porous substrates.

There is no adhesion on PE, PP, PTFE (Teflon®) and bituminous substrates. We recommend a preliminary adhesion test on any substrate.

Joint dimensions

Min. width for joints: 5 mm
Max. width for joints: 30 mm
Min. depth for joints: 5 mm

Recommendation sealing jobs: joint width = 2×10^{-1} x joint depth.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

 Soudal NV
 Everdongenlaan 18 - 20
 B-2300 Turnhout, Belgium

 Tel: +32 (0)14-42.42.31
 Fax: +32 (0)14-42.65.14
 www.soudal.com





Sanitary Silicone Turbo

Revision: 3/08/2020 Page 2 from 2

Application method

Application method: With manual- or

pneumatic caulking gun.

Cleaning: Clean with White Spirit or Soudal Surface Cleaner immediately after use (before

curing).

Finishing: With a soapy solution or Soudal Finishing Solution before skinning. Repair: With the same material.

Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult the packaging label for more information.

Remarks

- Do not use on natural stones like marble, granite,...(staining). Use Soudal Silirub MA or Silirub+ S8800 for this application.
- Because of the acid nature, certain metals (eg copper, lead) can be affected.
- Direct contact with the secondary sealing of insulating glass units (insulation) and the PVB-film of safety glass must be avoided.
- Sanitary Silicone Turbo can be stressed with water only 1 hour after application.
 Other direct stress is to be avoided the first hours after application.
- The sanitary formula should not replace regular cleaning of the joint. Excessive contamination, deposits or soap remainigs will stimulate the development of fungi.
- A total absence of UV can cause a color change of the sealant.
- In an acid environment or in a dark room, a white sealant can slightly turn yellow.
 Under the influence of sunlight it will turn back to its initial colour.
- When finished with a finishing solution or soapy solution, make sure that the surfaces are not touched by this solution. This will cause the sealant not to adhere to that surface. Therefore we recommend to only dip the finishing tool in this solution.
- We strongly recommend not to apply the Finishing Solution in full sunlight as it will dry very fast in these circumstances.

- Do not use in applications where continuous water immersion is possible.
- When using different reactive joint sealants, the first joint sealant must be completely hardened before the next one is applied.

Environmental clauses

Leed regulation:

Sanitary Silicone Turbo conforms to the requirements of LEED. Low –Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOC-content.

Liability

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

 Soudal NV
 Everdongenlaan 18 - 20
 B-2300 Turnhout, Belgium

 Tel: +32 (0)14-42.42.31
 Fax: +32 (0)14-42.65.14
 www.soudal.com